

**CERTIFICATE****No. A/16-612848 Rev 00**
Date 2016-10-26 Page 1/3INSPECTION CERTIFICATE acc to
EN 10204 3.1Processkontroll Items AB
Box 2088
444 02 STORA HÖGA
SWEDENINSPECTION STAMP
QA-TUBE

Customer References		Sandvik References	
754029	Customer order 2016-10-26	Order No. 458022	Subs No. 618631
003-00991 ITEMS		ABSMT No. 300-53984	Dispatch note 31744/54
		C.Code 15	

Material description	Steel/material Designations
SEAMLESS STAINLESS COLD FINISHED HYDRAULIC TUBING	Sandvik AISI 3R60 TP316/TP316L EN no 1.4435
Steel making process Electric furnace	

Technical requirements
ASTM A-213-15C AW, ASME SA-213-ED-15 AW, ASTM A-269-15A NACE MR0175/ISO 15156-3:2015, NACE MR0103/ISO 17495:2015 PED 2014/68/EU EN 10216-5 TC1 HRB MAX 80

EXTENT OF DELIVERY								
It	Product designation	Heat	Lot	Pieces	Kg	M		
03	THT-3R60-16-1.5 16.00 X 1.50	048295	94579	5	16.0	30.00		
				Total	5	16.0 30.00		
KEY TO HEAT		KEY TO LOT						
Heat Code	Heat No.	Lot Code	Lot No.					
048295	545826	94579	182697					
TEST RESULTS								
Chemical composition (weight%)								
Heat	C	Si	Mn	P	S	Cr	Ni	Mo
048295	0.021	0.40	1.66	0.033	0.007	17.31	13.10	2.64
	N							
048295	0.042							
Chemical composition, product (weight%)								
Heat	C	Si	Mn	P	S	Cr	Ni	Mo
048295	0.020	0.40	1.66	0.033	0.005	17.34	13.08	2.62
	N							
048295	0.040							
Quality assurance - Lars-Åke Bergqvist / QA-manager MTC Service / Certificates								

**CERTIFICATE****No. A/16-612848****Rev 00****Date 2016-10-26****Page 2/3****Tensile test at room temperature**

Lot	Yield strength		Tensile strength	Elongation	
	MPa	MPa	MPa	%	%
	Rp0.2	Rp1.0	Rm	A	2"
94579	278	318	558	42	44
	286	324	565	45	47

Hardness test

Lot	Min	Max
94579	71	74

Following controls/tests have been satisfactorily performed:

- Flattening test.
- Flaring test
- PMI-test.
- Intergranular corrosion test acc to ASTM A-262 PR.E
- Leak test: Eddy current test acc to EN ISO 10893-1, ASME SA-1016.
- Visual inspection and dimensional control.

Heat Treatment:

Solution annealed at a temperature of Min 1040° C and quenched.

Marking:

SANDVIK 3R60 ASTM A213/A269 ASME SA213 COLD EN10216-5 TC1 EN10305-1 TP 316/TP 316L EN 1.4435 CFA SML NDE 16.00 X 1.50 MM HT 545826 SG LOT 182697 MADE BY SANDVIK *QA-TUBE*

The raw material is free from radioactive contamination.

Material free from mercury contamination.

No welding or weld repair.

Approved acc. AD 2000-Merkblatt W0 and certified acc. to Pressure Equipment Directive (2014/68/EU) by TUEV NORD; notified body, reg.no. 0045.

The number of tests are based on the size of the manufacturing lot before cutting to finished lengths.

The delivered products comply with the specifications and requirements of the order.

The material is manufactured according to a Quality system, approved and registered to ISO 9001:2008.

No unauthorized alterations. The contents of this Inspection Certificate may not be modified or revised in any way without the prior written approval of AB Sandvik Materials Technology. Unauthorized alterations to the Inspection Certificate, including introduction of false, fictitious or fraudulent statements or entries, may be punishable by fines, imprisonment, or both. This Inspection Certificate may be copied only in the manner and for the purposes specified in Section 6 of EN 10204:2004. Contravention of this notice will be prosecuted to the fullest extent of applicable law.

The certificate is produced with EDP and valid without signature.



CERTIFICATE

No. A/16-612848

Rev 00

Date 2016-10-26

Page 3/3

TEST RESULTS TRANSFERRED FROM CERTIFICATE NO 182697