

**CERTIFICATE****No. A/17-693557 Rev 00**
Date 2017-10-19 Page 1/3INSPECTION CERTIFICATE acc to
EN 10204 3.1Processkontroll Items AB
Box 2088
444 02 STORA H@GA
SWEDENINSPECTION STAMP
QA-TUBE

Customer References		Sandvik References	
755463	Customer order 2017-09-27	Order No. 492364	Subs No. 637615
003-00991 ITEMS		ABSMT No. 300-69717	ABSMT Dispatch note 06931/54 C.Code 15

Material description	Steel/material Designations
SEAMLESS STAINLESS COLD FINISHED HYDRAULIC TUBING	Sandvik AISI 3R60 TP316/TP316L EN no 1.4435
Steel making process Electric furnace	

Technical requirements
ASTM A-213-17 AW, ASME SA-213-ED-15 AW, ASTM A-269-15A NACE MR0175/ISO 15156-3:2015, NACE MR0103/ISO 17945:2015 PED 2014/68/EU EN 10216-5 TC1 HRB MAX 80

EXTENT OF DELIVERY								
It	Product designation	Heat	Lot	Pieces	Kg	M		
01	THT-3R60-10-1 10.00 X 1.00	048486	31907	30	42.0	180.00		
				Total	30	42.0	180.00	
KEY TO HEAT								
Heat Code		Heat No.						
048486		548641						
TEST RESULTS								
Chemical composition (weight%)								
Heat	C	Si	Mn	P	S	Cr	Ni	Mo
048486	0.027	0.37	1.59	0.032	0.0080	17.18	13.10	2.62
	N							
048486	0.038							
Quality assurance - Lars-Åke Bergqvist / QA-manager MTC Service / Certificates								

**CERTIFICATE**

No. A/17-693557 Rev 00
Date 2017-10-19 Page 2/3

Chemical composition, product (weight%)

Heat	C	Si	Mn	P	S	Cr	Ni	Mo
048486	0.020	0.39	1.62	0.032	0.0050	17.20	13.07	2.62
	N							
048486	0.038							

Tensile test at room temperature

Lot	Yield strength		Tensile strength	Elongation	
	MPa	MPa	MPa	%	%
	Rp0.2	Rp1.0	Rm	A	4D
31907	335	372	594	46	43

Hardness test

Lot	Min	Max
	HRB	HRB
31907	76	78

Following controls/tests have been satisfactorily performed:

- Flattening test.
- Flaring test
- PMI-test.
- Intergranular corrosion test acc to ASTM A-262 PR.E and EN ISO 3651-2A
- Leak test: Eddy current test acc to EN ISO 10893-1, ASME SA-1016.
- Visual inspection and dimensional control.

Heat Treatment:

Solution annealed at a temperature of Min 1040° C and quenched.

Marking:

SANDVIK 3R60 ASTM A213/A269 ASME SA213 COLD EN10216-5 TC1 EN10305-1 AW EN 1.44 35 TP316/316L CFA SML NDE 10.00 X 1.00 MM HT 548641 SS LOT 31907 MADE IN SWEDEN *QA-TUBE*

The raw material is free from radioactive contamination.

Material free from mercury contamination.

No welding or weld repair.

Approved acc. AD 2000-Merkblatt W0 and certified acc. to Pressure Equipment Directive (2014/68/EU, Annex 1 para 4.3) by TUEV NORD; notified body, reg.no. 0045.

The number of tests are based on the size of the manufacturing lot before cutting to finished lengths.

The delivered products comply with the specifications and requirements of the order.

The material is manufactured according to a Quality system, approved and registered to ISO 9001:2008.



No unauthorized alterations. The contents of this Inspection Certificate may not be modified or revised in any way without the prior written approval of AB Sandvik Materials Technology. Unauthorized alterations to the Inspection Certificate, including introduction of false, fictitious or fraudulent statements or entries, may be punishable by fines, imprisonment, or both. This Inspection Certificate may be copied only in the manner and for the purposes specified in Section 6 of EN 10204:2004. Contravention of this notice will be prosecuted to the fullest extent of applicable law.

The certificate is produced with EDP and valid without signature.