

**CERTIFICATE****No. A/18-736503****Rev 00****Date 2018-04-17****Page 1/3**INSPECTION CERTIFICATE acc to
EN 10204 3.1Processkontroll Items AB
Box 2088
444 02 STORA H@GA
SWEDENINSPECTION STAMP
QA-TUBE

Customer References		Sandvik References	
756295	Customer order 2018-04-09	Order No. 510436	Subs No. 649311
003-00991 ITEMS		ABSMT No. 300-79293	ABSMT Dispatch note 19503/54
		C.Code 15	

Material description	Steel/material Designations
SEAMLESS STAINLESS COLD FINISHED HYDRAULIC TUBING	Sandvik AISI 3R60 TP316/TP316L EN no 1.4435
Steel making process Electric furnace	

Technical requirements
ASTM A-213-17 AW, ASME SA-213-ED-17 AW, ASTM A-269-15A NACE MR0175/ISO 15156-3:2015, NACE MR0103/ISO 17945:2015 PED 2014/68/EU EN 10216-5 TC1 HRB MAX 80

EXTENT OF DELIVERY						
It	Product designation	Heat	Lot	Pieces	Kg	M
01	THT-3R60-12-1	551759	39045	34	58.0	204.00
	12.00 X 1.00	551672	39955	66	112.0	396.00
		Total		100	170.0	600.00

TEST RESULTS								
Chemical composition (weight%)								
Heat	C	Si	Mn	P	S	Cr	Ni	Mo
551672	0.019	0.43	1.63	0.027	0.009	17.29	13.07	2.62
551759	0.020	0.39	1.60	0.031	0.009	17.26	13.07	2.63
	N							
551672	0.048							
551759	0.036							

Quality assurance - Sofia Åkesson / Q-Manager
MTC Service / Certificates

**CERTIFICATE**

No. A/18-736503 Rev 00
Date 2018-04-17 Page 2/3

Chemical composition, product (weight%)

Heat	C	Si	Mn	P	S	Cr	Ni	Mo
551672	0.022	0.44	1.64	0.028	0.008	17.30	13.09	2.64
551759	0.020	0.40	1.60	0.031	0.007	17.27	13.10	2.64
	N							
551672	0.050							
551759	0.040							

Tensile test at room temperature

Lot	Yield strength		Tensile strength	Elongation	
	MPa	MPa	MPa	%	%
	Rp0.2	Rp1.0	Rm	A	2"
39045	327	373	597	46	42
39955	314	353	594	52	50

Hardness test

Lot	Min	Max
	HRB	HRB
39045	75	77
39955	72	76

Following controls/tests have been satisfactorily performed:

- Flattening test.
- Flaring test
- 100% PMI-test.
- Intergranular corrosion test acc to ASTM A-262 PR.E and EN ISO 3651-2A
- Leak test: Eddy current test acc to EN ISO 10893-1, ASME SA-1016.
- Visual inspection and dimensional control.

Heat Treatment:

Solution annealed at a temperature of Min 1040° C and quenched.

Marking:

SANDVIK 3R60 ASTM A213/A269 ASME SA213 COLD EN10216-5 TC1 EN10305-1 AW EN 1.44 35 TP316/316L CFA SML NDE 12.00 X 1.00 MM HT 551759 SS LOT 39045 MADE IN SWEDEN *QA-TUBE*

SANDVIK 3R60 ASTM A213/A269 ASME SA213 COLD EN10216-5 TC1 EN10305-1 AW EN 1.44 35 TP316/316L CFA SML NDE 12.00 X 1.00 MM HT 551672 SS LOT 39955 MADE IN SWEDEN *QA-TUBE*

The raw material is free from radioactive contamination.

Material free from mercury contamination.

No welding or weld repair.

Approved acc. AD 2000-Merkblatt W0 and certified acc. to Pressure Equipment Directive (2014/68/EU, Annex 1 para 4.3) by TUEV NORD; notified body, reg.no. 0045.

The number of tests are based on the size of the manufacturing lot before cutting to finished lengths.

The delivered products comply with the specifications and requirements of the order.



The material is manufactured according to a Quality system, approved and registered to ISO 9001:2008.

No unauthorized alterations. The contents of this Inspection Certificate may not be modified or revised in any way without the prior written approval of AB Sandvik Materials Technology. Unauthorized alterations to the Inspection Certificate, including introduction of false, fictitious or fraudulent statements or entries, may be punishable by fines, imprisonment, or both. This Inspection Certificate may be copied only in the manner and for the purposes specified in Section 6 of EN 10204:2004. Contravention of this notice will be prosecuted to the fullest extent of applicable law.

The certificate is produced with EDP and valid without signature.