Order : 843590 Index : 190806B2200

Index: 190806B2200 Ref.:

Article: 16X 2 S A269/A213M D4/T3 316(L)* 6 (-

Delivery: 0085600964/000010 Quantity: 402,000 M

Heat : QY1802-019

This document is reproduced by a computerized system and is identical to the original



A NORSOK APPROVED & DNV APPROVAL OF MANUFACTURER, AN ISO 9001:2015, ISO 14001:2015, BS OHSAS 18001:2007, PED & ADW / AD - 2000 - W0 Certified Company

MFG. & EXPORTER OF STAINLESS STEEL SEAMLESS & WELDED PIPES / TUBES / U-TUBES
GOVT. RECOGNISED EXPORT HOUSE
CIN: 1127106G12006PTC049217

		GO	VT. RECOGN	HSED EXPO	RT HOUSE	CI	N: U2710	06GJ200	6PTC04921	7			
								F/QAC/12=RFV.01					
T.C.NO:-MT										CPL/2019-20/0085A11			
INSPECTION CERTIFICATE AS PER EN 10204 - 3,2 DATE :-29.													
CUSTOM	ER NAME :- M/s	VAN LEEUWEI	N STAINLESS B	v	 				L				
P.O. NO.	:- 3491391	· · · · · · · · · · · · · · · · · · ·							DATE :-04.1	0.2018			
O.A.NO. :- 2018/10/11144_BA/EXP DATE :-04.										0.2018			
QAP.NO. :- 11144/EXP_2 REV.00 DATE :-08.0										2.2019			
PRODUC	T :- AUSTENITI	C S. S. SEAMLES	S (POLISHED	GRIT-240) TUI	BE (COLD FINI	SHED, BRIGH	IT ANNEAL	ED)-MELTI	NG PROCESS:-	E.A.F.+A.O.D.			
MAT.SPI	C.:- ASTM A 269	-15a, ASTM A	213/213M-18	b, TP 316/316	L, SA 213 OF A	SME SEC-II,	PART-A, ED	ITION 201	7, ASTM/ASMI	E A/SA 1016/10	16M,		
	EN 10216-5, T	C-1, GRADE 1.	4401/1.4404,	EN ISO 1127 D	4/T3, NACE M	R 0175/ISO	15156-3: 2	015, NACE	MR 0103/ISO	17495-1: 2016	,		
	VAN LEEUWE	N NEW SPECIF	CATION FOR T	TUBE & PED 20	014/68/EU, Al	2000, W2							
w.o.	HEAT NO.	DIMENSIONS							NO. OF PCS	TOTAL METER			
SR. NO.													
18	QY1802-019	16.00 MM OD X 2.00 MM THK X 6000 MM LONG									1860.000		
18 CHEMICAL TEST %													
	HEAT NO.	s	С	Si	Mn	P	S	Ni	Cr	Мо	N	Ti	
SR. NO.			0.030	1.000	2.000	0.040	0.015	10.000	16.500	2.000	0.100		
			MAX	MAX	MAX	MAX	MAX	13.000	18.000	2.500	MAX		
13	QY1802-019	Н	0.021	0.370	1.250	0.033	0.004	10.170	16.580	2.110	0.008		
	Q.1002 013	P	0.018	0.401	1.274	0.031	0.006	10.179	16.558	2.119	0.009		
	·····					ICAL TESTS			,	·	·	,	
SR. NO.	TENSILE STRENGTH Rm N/mm²	YIELD STRENGTH	YIELD STRENGTH	ELON. A%, G.L=5.65√A,	ELON. A%, G.L= 50MM,	HARDNESS TEST	FLARING	FLANGE TEST	RING EXPANSION TEST	FLATTENING TEST	RING TENSILE TEST	OTHER	
		Rp 0.2%	Rp 1.0%	G.W= FULL			TEST					TEST	
		N/mm²	N/mm²	SPECIMEN	SPECIMEN	MAX							
REQ.	530 - 690	276 MIN		L=40% MIN	L=35%(MIN)	85 HRB							
13	603.00	314.00	340.00	60	62	72-74	ок	N.A	N.A	ок	N.A	N.A	
	594.00	306.00	335.00	58	59						L	l	
REMARK													
	G ON PRODUCT :												
	EATMENT :- BRI												
	TEST PRESSURE						0 ppm & HO	LDING TIM	E 10 SEC. MIN)			
	IRRENT TEST :- A												
	TEST ACCORDANG				·				FOUND SATIS	FACTORY.			
	IANICAL TEST CA												
	UCT ANALYSIS CA												
	EDDY CURRENT							ACTORY.					
	HYDRO TEST CA												
·	PMI TEST CARR							ODV					
	DIMENSION AND					GL - FOUND	SATISPACT	UKY.					
	ERIAL IS FREE FR WITNESSED TUBI					EC ADECINO	LE CTAMPE	D/ELECTR	CTCUED) E	D IDENTIFICAT	ION		
	ROVED ACC. TO A				***						1011.		
-	RESSURE EQUIPM					<u>'</u>	<u> </u>				0/18		
	SPECIFICATION, P											F.	
1.01E:- 3=	- I BOIL TON, P	- PROTOCE VINE	1313, 11= HEAT		- GAUGE LENGII	., u. 17 - UAUU	. ** ID I II, L=	2011011001	The second	- 22WE, 1107 = 1101	www.		
	REDINMENT	DNV GL		P.O. ITEM :- COMPLETE			Authoriagar CHATEN			PARTY			
	4NSPECTOR'S/					·		ANAGERT	·····		NSPECTOR	(Q.A.)	
WE HER	EBY CERTIFY TH	AT THE MATE	RIAL IS AS PER	SIZE & SPECIF	ICATION MEN	TIONED IN C	RDER, ALL	TEST RESU	JLT ARE ACCE	PTABLE.			

Regd. Office & Works: Survey No. 105/106, Nr. 66 KV Sub-Station, Chhatral-Pansar Road, Ahmedabad-Mehsana Highway, Chhatral-382729, Ta. Kalol, Dist. Gandhinagar, Gujarat, INDIA. Export Phone No. +91 99091 98877, F: +91 2764 234477, E: export@maximtubes.com
Admin. Office: B-92, Riviera Antilia, Nr. Pinnacle Corporate Road, Prahladnagar,
Vejalpur, Ahmedabad, Gujarat-380051, INDIA.